

**Specification for Precast, Prestressed Concrete Piles,
ANSI/PCI 142-24, Errata
August 2024**

The errata published herein are intended to supplement, revise, or clarify the information provided in the standard. PCI suggests that you mark the changes in your copy so that your standard is as accurate as possible. New errata since the previous version published in May 2024 are marked with a vertical bar in the margin.

As this edition of the standard is used, additional errata may be discovered. You are urged to notify PCI of any potential errata for committee review. You are also encouraged to send any questions or comments to PCI regarding the material in the standard and suggested improvements or clarifications. Please direct your comments to PCI at standards@pci.org.

Page 10, Section 4.4.5: Replace

(b) The allowable tensile stress for driving in normal environments shall be f_{pc} .

with

(b) The allowable tensile stress for driving in normal environments shall be $3\sqrt{f'_c} + f_{pc}$.